235 Snowhite REINFORCED WATER ACTIVATED TAPE

INTERTAPE POLYMER GROUP TECHNICAL DATA SHEET

DESCRIPTION

3-Way fiberglass reinforced snowhite carton sealing tape, manufactured with water activated adhesive.

PRODUCT APPLICATION

Used for two strip sealing cartons top and bottom. Works well on recycled cartons, and non-unitized loads. Recommended for use on light weight to average cartons up to 20 pounds.



intertape polymer group™

3647 Cortez Road West | Bradenton, FL 34210 | USA Customer Service: 800.IPG.8273 | 800.474.8273 Tape Technical Service: 877.447.4832

www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 12/10/2012

CONSTRUCTION (PER 3,000 SQUARE FEET):

CONSTRUCTION (FER 3,000 SQU	ANE FEELJ:
Top Ply:	25 Lb. White Paper (virgin
	fibers)
Bottom Ply:	23 Lb. Natural Kraft Paper
	(virgin fibers)
Laminating Adhesive:	13.5 Lb. High Melt Index
	Polypropylene Based Co-
	Polymer
Remoistenable Adhesive:	15 Lb. Chemically Grafted
	Starch Based Copolymer
	Adhesive, Designated as
	S3911
MD Reinforcement:	1.92 Lb. (1-1-1-1) 110
	Fiberglass (per 72mm), 1/2"
	spacing
CD Reinforcement:	1.34 Lb. (1-1-1) 150
	Fiberglass, 1.20" spacing,
	37 degree angle
Total Basis Weight:	79.8 Lb.
PHYSICAL PROPERTIES:	
Caliper (mils):	5.9
MD Tensile (Lbs./in.):	64
CD Tensile (Lbs./in.):	27
ADHESION (WATER AT RECOMMI	ENDED 110°F):
Fipago:	
2/0	49
2/1	76
5/0	74
15/0	89
McClaurin:	87

