## **285 Natural** REINFORCED WATER ACTIVATED TAPE

# INTERTAPE POLYMER GROUP TECHNICAL DATA SHEET

#### DESCRIPTION

Highest tensile strength 3-Way fiberglass reinforced natural kraft carton sealing tape, manufactured with water activated adhesive, capable of meeting the demanding requirements of the "old Rule 41" specifications.

#### **PRODUCT APPLICATION**

Used for two strip sealing cartons top and bottom. Works well on recycled cartons and non-unitized loads. Recommend using on heavyweight cartons over 90 pounds.



intertape polymer group™

3647 Cortez Road West | Bradenton, FL 34210 | USA Customer Service: 800.IPG.8273 | 800.474.8273 Tape Technical Service: 877.447.4832

www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 12/10/2012

### CONSTRUCTION (PER 3,000 SQUARE FEET):

Top Ply: Bottom Ply: Laminating Adhesive: Remoistenable Adhesive:	40 Lb. Natural Kraft Paper 40 Lb. Natural Kraft Paper 23 Lb. High Melt Index Polypropylene Based Co- Polymer 20 Lb. Chemically Grafted Starch Based Copolymer Adhesive, Designated as S3911
MD Reinforcement	5.33 Lb. (2-2-1-1-2-2) 75 Fiberglass (per 3"), ½" spacing
CD Reinforcement	4.71 (1-1-1) 75 Fiberglass,
Total Basis Weight:	0.68" spacing, 25º angle 133.0 Lb.
<b>PHYSICAL PROPERTIES:</b>	
<b>Caliper</b> (mils): <b>MD Tensile</b> (Lbs./in.):	10.5 92
<b>CD Tensile</b> (Lbs./in.):	59
ADHESION (WATER AT RECOMMENDED 110°F): Fipago:	
2/0	37
2/1 5/0	57 67
15/0	86
McClaurin:	85